

#### 1. Product Description

Product description	: PROFT UNIVERSAL SILICONE is one component, elastic, solvent free 100% silicone. It cures by humidity.
Product form	: Mixture
Trade name	: PROFT UNIVERSAL SILICONE
Use of the substance/mixture	: Adhesives, sealants
Recommended use	: Industrial use Professional uses Consumer use
Type of product	: Adhesives, sealants

#### **Manufacturer/Supplier:**

**Yaşar Teknik Yapı Malzemeleri Dış. Tic. A.Ş**  
İnönü Mah. Fatih Sultan Mehmet Cad. No:3  
Gebze / KOCAELİ - TURKEY  
Phone: +90 (850) 307 74 74  
[www.yasarteknik.com.tr](http://www.yasarteknik.com.tr)

#### 2. Characteristics

Characteristics	: Easy to apply Highly adhesive High-end DIY-quality Non-tacky surface Easy gunnability Non-yellowing Shrinkage <15%. Excellent appearance High transparency
-----------------	--

#### 3. Application

- Gluing parquets, mounting woods, doors, windows, panels and mouldings.
- Using for glass, wooden furnitures, cupboards, wardrobes, staircases, mounting and fixing decorative timbers
- It is used for mounting and fixing decorative woods.

#### 4. Application Instructions

- Application temperature is between +5 °C to +40 °C.
- Make sure the surface to be applied is dry and clean, free of dust, dirt, rust and grease
- Cut the cartridge/sausage tip and place it in the gun
- Apply the silicone over the surface in strip form
- Clean any silicone residue simply with soapy water
- Joint width and depth ratio should be about 2:1

#### 5. Technical Specifications (@ 23 °C 50% RH)

Physical state	: Solid
Chemical Basis	: Acetoxy.
Appearance	: Paste.
Odour	: characteristic
Curing System	: Moisture
Skin Forming Time	: 5 – 20 minutes
Curing Rate	: 4 – 5 mm/day
Elongation at Break	: 250 % ±30
Tensile Strength	: 0.5 N/mm <sup>2</sup> ±1
Hardness Shore A	: 18

Density	: 0.96 – 0.98 g/cm <sup>3</sup> @23°C
Viscosity, kinematic	: Not applicable
Thermal Resistance	: -40 – 180 °C
Application Temperature	: 5 → 40 °C

## 6. Packaging

<b>Packaging</b>	: Original packaging
<b>Colour</b>	: Transparent. Black. white. brown. Aluminium. Grey. Beige.

Cartridge 280 ml	Package 24 pcs/ctn
Cartridge 310 ml	Package 24 pcs/ctn
Sausage 600 ml	Package 20 pcs/ctn

## 7. Shelf Life and Storage

Storage conditions	: Protect from moisture. Store in a dry place. Store in a closed container. Store in a well-ventilated place. Keep cool.
Storage temperature	: 0 → 35 °C

Cartridge 280 ml	18 months (after production date, if stored at room temperature)
Cartridge 310 ml	18 months (after production date, if stored at room temperature)
Sausage 600 ml	18 months (after production date, if stored at room temperature)

## 8. Health and Safety

Adverse physicochemical, human health and environmental effects	: To our knowledge, this product does not present any particular risk, provided it is handled in accordance with good occupational hygiene and safety practice
First-aid measures after inhalation	: Remove person to fresh air and keep comfortable for breathing.
First-aid measures after skin contact	: Wash skin with plenty of water.
First-aid measures after eye contact	: Rinse eyes with water as a precaution.
First-aid measures after ingestion	: Call a poison center or a doctor if you feel unwell.
Other medical advice or treatment	: Treat symptomatically.
Hand protection	: Protective gloves
Eye protection	: Safety glasses
Skin and body protection	: Wear suitable protective clothing
Respiratory protection	: In case of insufficient ventilation, wear suitable respiratory equipment

## 9. Remarks

No information available

## 10. Standards and Certificates

Standards and Certificates	: EN 15651-1 EN 15651-2
----------------------------	----------------------------

Technical Data Sheet

*DISCLAIMER OF LIABILITY* The information in this SDS was obtained from sources which we believe are reliable. However, the information is provided without any warranty, express or implied, regarding its correctness. The conditions or methods of handling, storage, use or disposal of the product are beyond our control and may be beyond our knowledge. For this and other reasons, we do not assume responsibility and expressly disclaim liability for loss, damage or expense arising out of or in any way connected with the handling, storage, use or disposal of the product. This SDS was prepared and is to be used only for this product. If the product is used as a component in another product, this SDS information may not be applicable